



CPAR P-58 AO

MEDIUM-CHAIN CHLORINATED ALPHA OLEFIN

PROPERTY	TYPICAL RESULT
Color, Gardner	2
Chlorine, % by Weight	59
Specific Gravity, 25 C	1.39
Density, lbs/gal	11.6
Viscosity, SUS @ 210 F	170
Viscosity, SUS @ 100 F	17500
Viscosity, cSt @ 100 C	38
Viscosity, cSt @ 40 C	3200
Viscosity, Poise @ 25 C	280
Carbon Chain Length	C14


CPAR P-58 AO Applications:

Flame retardant and plasticizer in polymers. Flame retardant, plasticizer and lubricant in adhesives, caulks, sealants, and coatings. Additives in lubricants including metalworking fluids.

Flame retardant and plasticizer in rubber. Flame retardant and waterproofer in textiles.

www.QualiceLLC.com

11 E.V. Hogan Drive, Hamlet, NC 28345 USA

Qualice, LLC is a true pioneer in the domestic additive manufacturing industry, dedicated to utilizing the newest technology in our production process. At Qualice we are committed to providing the highest quality products with a pledge of uncompromised service. Our entire line of  liquid products are manufactured exclusively by Qualice in the USA.