



## CPAR P-56

### MEDIUM-CHAIN CHLORINATED PARAFFIN

PROPERTY	TYPICAL RESULT
Color, Gardner	2
Chlorine, % by Weight	56
Specific Gravity, 25 C	1.32
Density, lbs/gal	11.10
Viscosity, SUS @ 210 F	130
Viscosity, SUS @ 100 F	8400
Viscosity, cSt @ 100 C	27
Viscosity, cSt @ 40 C	1800
Viscosity, Poise @ 25 C	150
Carbon Chain Length	C14 - 16

#### CPAR P-56 Applications:


Flame retardant and plasticizer in polymers. Flame retardant, plasticizer and lubricant in adhesives, caulks, sealants, and coatings. Additives in lubricants including metalworking fluids.

Flame retardant and plasticizer in rubber. Flame retardant and waterproofer in textiles.

[www.QualiceLLC.com](http://www.QualiceLLC.com)

11 E.V. Hogan Drive, Hamlet, NC 28345 USA

---

Qualice, LLC is a true pioneer in the domestic additive manufacturing industry, dedicated to utilizing the newest technology in our production process. At Qualice we are committed to providing the highest quality products with a pledge of uncompromised service. Our entire line of  liquid products are manufactured exclusively by Qualice in the USA.