



Cpar P-50 AO MEDIUM CHAIN CHLORINATED PARAFFIN

PROPERTY	TYPICAL RESULT
Color, Gardner	1
Chlorine, % by Weight	48
Specific Gravity, 25 C	1.22
Density, lbs/gal	10.2
Viscosity, SUS @ 210 F	280
Viscosity, SUS @ 100 F	10000
Viscosity, cSt @ 100 C	60
Viscosity, cSt @ 40 C	2100
Viscosity, Poise @ 25 C	110
Carbon Chain Length	C24-28

CPAR P-50 AO Applications

- Flame retardant and plasticizer in polymers.
- Flame retardant, plasticizer and lubricant in adhesives, caulks, sealants, and coatings.
- Additive in lubricants including metalworking fluids.
- Flame retardant and plasticizer in rubber.
- Flame retardant and waterproofer in textiles.



www.Qualicellc.com
11 E.V. Hogan Drive, Hamlet, NC 28345
USA