



## Cpar P-52

### MEDIUM CHAIN CHLORINATED PARAFFIN

PROPERTY	TYPICAL RESULT
Color, Gardner	1
Chlorine, % by Weight	52
Specific Gravity, 25 C	1.28
Density, lbs/gal	10.7
Viscosity, SUS @ 210 F	71
Viscosity, SUS @ 100 F	1575
Viscosity, cSt @ 100 C	14
Viscosity, cSt @ 40 C	335
Viscosity, Poise @ 25 C	17
Carbon Chain Length	C14-16

### CPAR P-52 Applications

- Flame retardant and plasticizer in polymers.
- Flame retardant, plasticizer and lubricant in adhesives, caulks, sealants, and coatings.
- Additive in lubricants including metalworking fluids.
- Flame retardant and plasticizer in rubber.
- Flame retardant and waterproofer in textiles.



[www.Qualicellc.com](http://www.Qualicellc.com)  
11 E.V. Hogan Drive, Hamlet, NC 28345  
USA