



Cpar W-45

VERY LONG CHAIN CHLORINATED PARAFFIN

PROPERTY	TYPICAL RESULT
Color, Gardner	2
Chlorine, % by Weight	45
Specific Gravity, 25 C	1.20
Density, lbs/gal	10.0
Viscosity, SUS @ 210 F	270
Viscosity, SUS @ 100 F	9000
Viscosity, cSt @ 100 C	57
Viscosity, cSt @ 40 C	2000
Viscosity, Poise @ 25 C	100
Carbon Chain Length	C21+

CPAR W-45 Applications

- Flame retardant and plasticizer in polymers.
- Flame retardant, plasticizer and lubricant in adhesives, caulks, sealants, and coatings.
- Additive in lubricants including metalworking fluids.
- Flame retardant and plasticizer in rubber.
- Flame retardant and waterproofer in textiles.



www.Qualicellc.com
11 E.V. Hogan Drive, Hamlet, NC 28345
USA